

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6 :
C25C 7/06, 1/16

A1

(11) International Publication Number: WO 96/41039

(43) International Publication Date: 19 December 1996 (19.12.96)

(21) International Application Number: PCT/CA96/00366

(22) International Filing Date: 7 June 1996 (07.06.96)

(30) Priority Data:
08/478,215 7 June 1995 (07.06.95) US

(71) Applicant (for all designated States except US): COMINCO LTD. [CA/CA]; 200 Burrard Street, Vancouver, British Columbia V6C 3L7 (CA).

(72) Inventors; and

(75) Inventors/Applicants (for US only): GONZALEZ DOMINGUEZ, Jose Alberto [MX/CA]; 1913 Robin Avenue, P.O. Box 375, Fruitvale, British Columbia V0G 1L0 (CA). MAKWANA, Dilipkumar, Devjibhai [CA/CA]; 919 - 7th Street, P.O. Box 442, Montrose, British Columbia V0G 1P0 (CA).

(74) Agent: REYNEKE, Russell; Two Bentall Centre, Suite 700, 555 Burrard Street, Vancouver, British Columbia V7X 1M8 (CA).

(81) Designated States: AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).


Published

With international search report.

(54) Title: REDOX CONTROL IN THE ELECTRODEPOSITION OF METALS

(57) Abstract

In one embodiment, a method of electrowinning a metal from an electrolyte comprises the steps of measuring the redox potential of the electrolyte to obtain a measured value, comparing the measured value with a predetermined optimum value and adding a redox agent to the electrolyte to adjust the redox potential of the electrolyte to the optimum value. One embodiment of apparatus (10) for carrying out the method comprises a redox potential measuring device (20) having a housing for the flow of electrolyte therethrough and including a pair of electrodes (22, 24) for measuring the redox potential of an electrolyte flowing through the housing to produce an output measurement value and a redox controller (26) responsive to the output measurement value for controlling the addition of redox agent to the electrolyte of an electrolysis cell (12).



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AM	Armenia	GB	United Kingdom	MW	Malawi
AT	Austria	GE	Georgia	MX	Mexico
AU	Australia	GN	Guinea	NE	Niger
BB	Barbados	GR	Greece	NL	Netherlands
BE	Belgium	HU	Hungary	NO	Norway
BF	Burkina Faso	IE	Ireland	NZ	New Zealand
BG	Bulgaria	IT	Italy	PL	Poland
BJ	Benin	JP	Japan	PT	Portugal
BR	Brazil	KE	Kenya	RO	Romania
BY	Belarus	KG	Kyrgyzstan	RU	Russian Federation
CA	Canada	KP	Democratic People's Republic of Korea	SD	Sudan
CF	Central African Republic	KR	Republic of Korea	SE	Sweden
CG	Congo	KZ	Kazakhstan	SG	Singapore
CH	Switzerland	LJ	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovakia
CM	Cameroon	LR	Liberia	SN	Senegal
CN	China	LT	Lithuania	SZ	Swaziland
CS	Czechoslovakia	LU	Luxembourg	TD	Chad
CZ	Czech Republic	LV	Latvia	TG	Togo
DE	Germany	MC	Monaco	TJ	Tajikistan
DK	Denmark	MD	Republic of Moldova	TT	Trinidad and Tobago
EE	Estonia	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	UG	Uganda
FI	Finland	MN	Mongolia	US	United States of America
FR	France	MR	Mauritania	UZ	Uzbekistan
GA	Gabon			VN	Viet Nam

REDOX CONTROL IN THE ELECTRODEPOSITION OF METALS

FIELD OF THE INVENTION

5 This invention relates to the electrodeposition of a metal from an electrolyte. In particular, but not exclusively, the invention relates to the electrowinning of a metal, such as zinc from zinc sulphate solution, as well as the on line or off line cleaning of an
10 electrolysis cell or an electrode of the cell.

BACKGROUND OF THE INVENTION

15 In the electrolysis of metals various ionic species can become oxidized or reduced. Thus, unwanted chemical products can be produced. Some of these products precipitate and need to be removed mechanically. Furthermore, such unwanted oxidation-reduction processes can consume electrons that could otherwise be used for
20 the plating of metals, thus, reducing the efficiency of the electrowinning process.

 Typically, in the zinc electrowinning industry the Faradaic cathodic current efficiency (CE), i.e. the
25 portion of the current which is actually utilized for the plating of the zinc, ranges from about 88% to about 93%. The difference between this CE value and the 100% value is due to the unwanted evolution of hydrogen and the presence of unwanted redox couples that consume
30 electrons, such as $\text{Fe}^{2+}/\text{Fe}^{3+}$ and $\text{Mn}^{2+}/\text{Mn}^{3+}$.

 Another factor that affects the CE value is the anode quality and its electrochemical properties. In the electrowinning of zinc, Pb-Ag anodes are normally used.
35 These anodes develop a PbO_2 layer upon which O_2 evolution and other side reactions can take place. Among the most

important of these is the formation of MnO_2 . MnO_2 precipitates on the anode increasing the so-called anodic overpotential and it also precipitates in the cell. This requires frequent anode cleaning which involves the removal of the anodes and the mechanical cleaning thereof. The precipitates that accumulate at the bottom of the cell also need to be removed periodically. These operations often require a plant shutdown, unless expensive mechanized vacuum units are used.

It is an object of the present invention to alleviate the above-mentioned difficulties.

SUMMARY OF THE INVENTION

According to the invention there is provided an electrolysis process wherein an electric current is passed through an electrolyte to effect a chemical change, which includes the step of maintaining the redox potential of the electrolyte within a predetermined range of values by adding a redox agent to the electrolyte.

The process may further comprise the steps of continuously monitoring the redox potential of the electrolyte and adding said redox agent to maintain the redox potential of the electrolyte within said predetermined range of values.

The electrolysis process may comprise an electrowinning process, an electrorefining process or an electroplating process.

Also according to the invention there is provided a method of electrowinning a metal from an electrolyte comprising the step of maintaining the redox

potential of the electrolyte within a predetermined range of values by adding a redox agent to the electrolyte.

5 Further according to the invention there is provided a method of electrowinning a metal from an electrolyte comprising the steps of measuring the redox potential of the electrolyte to obtain a measured value; comparing said measured value with a predetermined optimum value; and adding a redox agent to the
10 electrolyte to adjust the redox potential of the electrolyte to said optimum value.

The term "redox agent" refers to either an oxidizing agent or a reducing agent.
15

Further according to the invention there is provided apparatus for controlling the redox potential of an electrolyte, comprising a redox potential measuring device for measuring the redox potential of an
20 electrolyte to produce an output measurement value; and a redox controller responsive to said output measurement value for controlling the addition of redox agent to the electrolyte of an electrolysis cell.

25 Also according to the invention there is provided a method of reducing the formation of an electrolysis product on an electrode of an electrolysis cell comprising the step of performing an electrolysis process in the cell with an electrolyte in which a redox
30 agent is added which counteracts the formation of said product.

Further according to the invention there is provided a method of cleaning an electrolysis cell of an
35 electrolysis product formed in the cell, comprising the step of performing an electrolysis process in the cell

with an electrolyte to which a redox agent is added which counteracts the formation of said product.

Further according to the invention there is
5 provided a method of reducing MnO_2 formation in an electrolysis cell in a zinc electrowinning process, comprising the steps of measuring the redox potential of the electrolyte to obtain a measured value; comparing the measured value with a predetermined optimum value; and
10 adding a redox agent to the electrolyte to adjust the redox potential of the electrolyte to the optimum value.

Also according to the invention there is
15 provided a method of reducing current efficiency loss in an electrolysis cell in a zinc electrowinning process, comprising the steps of measuring the redox potential of the electrolyte to obtain a measured value; comparing the measured value with a predetermined optimum value; and
20 adding a redox agent to the electrolyte to adjust the redox potential of the electrolyte to the optimum value.

Further objects and advantages of the invention will become apparent from the description of a preferred embodiment of the invention below.
25

BRIEF DESCRIPTION OF THE DRAWINGS

The single drawing is a flow diagram illustrating an electrowinning and redox control process
30 according to the invention.

DETAILED DESCRIPTION OF PREFERRED EMBODIMENT

With reference to the drawing, a system for
35 carrying out a process for the electrowinning of zinc

according to the invention is generally indicated by reference numeral 10.

5 The system 10 comprises a series of electrolytic cells 12, a reservoir 14 for overflow electrolyte ("hot spent") electrolyte from the cells 12, a series of cooling towers 16 for cooling the hot electrolyte from the reservoir 14 and a reservoir 18 for fresh electrolyte, as well as cold spent electrolyte from
10 the cooling towers 16.

 The system 10 further includes a redox potential measuring device 20 provided with a working electrode 22 and a reference electrode 24, a redox
15 controller 26 and a reservoir 28 for H_2O_2 . The reservoir 28 is connected to the reservoir 18 via a pump 30 which is controlled by the redox controller 26 responsive to redox potential measurements effected by the measuring device 20.

20

 The working electrode 22 is a platinum or a silver electrode. The reference electrode 24 is a commercially available calomel or silver/silver chloride electrode.

25

 The control of the redox potential can be effectively achieved only when the proper sensing electrodes are used. Platinum is very sensitive to small changes in the redox potential and abrupt changes in
30 value can be observed when this electrode is used. However, with the proper process control design, good redox control (within 50 mV) can be achieved. Graphite electrodes have a slower response than platinum and because of this do not display erratic readings. Thus,
35 when graphite is used, changes in redox potential are not as abrupt as those observed with platinum. Thus, a

- 6 -

preferred working electrode has been found to be graphite. In laboratory size electrowinning cells, when a graphite electrode is used, redox control can be achieved to within 20 mV.

5

The redox controller 26 comprises the required electronic circuitry and software for receiving and interpreting a signal representing the measured value from the measuring device 20 and to control the delivery of the required amounts of H_2O_2 to the reservoir responsive to the redox measurements by the measuring device 20.

The measuring device 20 is provided with a flow channel (not shown) for the flow of a feed stream of electrolyte therethrough. The electrodes 22 and 24 are exposed to the electrolyte flowing through the channel for measuring the redox potential of the feed stream. As indicated by the arrows 32 and 34, the electrolyte feed stream is circulated from the reservoir 14 containing the overflow (hot spent) electrolyte, which is essentially equivalent to the electrolyte in the cells 12.

The electrodes 22, 24 are connected through electrical connections 36 and 38 to the electronic circuitry of the redox controller 26.

In carrying out a zinc electrowinning process, the pregnant aqueous zinc solution plus the usual additives, which constitutes the "fresh electrolyte", is fed to the reservoir 18 where it is mixed with cold spent electrolyte from the cooling towers 16.

From the reservoir 18 the electrolyte is transferred to the electrolytic cells 12 where the electrodeposition of zinc takes place.

Spent electrolyte overflow from the cells 12 is received by the reservoir 14, from where the electrolyte is circulated through the redox measuring device 20.

There is a bleed of spent electrolyte from the reservoir 14, as indicated by the arrow 40, which in the conventional process for the recovery of zinc from ore or concentrate is recycled back to a leaching stage, where zinc is leached from the ore or concentrate by a suitable leach solution.

A part of the hot spent electrolyte in the reservoir 14 is transferred to the cooling towers 16 for cooling and recycle to the fresh electrolyte reservoir 18.

The redox controller 26 is in electrical contact, as indicated at 42, with the pump 30 for controlling the operation of the pump 30. The pump 30 pumps H_2O_2 from the reservoir 28 to the fresh electrolyte reservoir 18, as indicated by the arrow 44. It is desirable that the reducing agent being added be well mixed with the electrolyte prior to its addition to the electrowinning cells 12.

In operation, when the measured value of the redox potential from the measuring device 20 falls outside a predetermined optimum range, the redox controller 26 will activate the pump 30 to inject the required amount of H_2O_2 into the tank 18 to bring the measured value within the optimum range. The optimum range will depend on the particular system involved.

In particular, the optimum range is determined by aspects such as anodic and cathodic current density, the age of the anode, the composition and temperature of the electrolyte and the concentration of additives in the

electrolyte. The optimum range for each particular system therefore needs to be determined empirically.


Therefore, to implement this technology in the industrial environment, laboratory and plant tests need to be conducted in advance to identify the optimum redox potential values at which the electrowinning process needs to be run. In the preferred practice for one zinc electrowinning operation, the optimum redox value was found to be 1040 ± 50 mV (Pt vs H_2/H^+ electrode).

The H_2O_2 can be added in diluted or concentrated form, preferably in concentrations higher than 35% so that no significant amounts of water are added to the system.

The reaction between H_2O_2 and MnO_2 occurs without kinetic limitations according to the following equation:

$$MnO_2 + 2H^+ + H_2O_2 \rightarrow Mn^{2+} + 2H_2O + O_2$$

In addition, the following reaction can take place upon H_2O_2 addition:



Thus, by using a suitable reducing agent, such as H_2O_2 in the present example, unwanted chemical products such as MnO_2 , Mn^{3+} and Mn^{7+} can be continuously removed. The extent to which these reactions take place is controlled by control of the redox potential of the electrolyte. The invention therefore provides a process for the on line or off line cleaning of the cell and anode which increases plant availability and reduces the need for mechanical anode and cell cleaning. In addition, anode life is increased due to a decreased

frequency of short circuits caused by excessive or uneven anode coatings.

5 Instead of direct measurement of the redox potential an indirect measurement can also be used. For example, in situations where there is a correlation between redox potential and solution color, such as in zinc electrowinning from sulphate media, a colorimeter can be used for controlling redox potential, although
10 direct E_h measurement would be more precise.

 In laboratory tests which were carried out the electrolyte cells were run in series under galvanostatic conditions. Electrolyte temperature was controlled at
15 $37 \pm 1^\circ\text{C}$. Electrolyte was recirculated to rates equivalent to the displacement of 1 to 1.5 cell volumes per hour. The E_h of the electrolyte was measured using calibrated bright Pt - calomel electrode pairs. E_h values reported are referred to the H_2/H^+ electrode. The E_h was
20 controlled by adding diluted H_2O_2 ($\approx 3\%$) to the recirculating electrolyte. The E_h electrodes were placed in the cell overflow.

 The initial electrolyte was prepared from
25 purified zinc electrolyte and reagent grade sulphuric acid. The concentrations of Zn and H_2SO_4 were maintained constant by neutral feed additions and continuous electrolyte removal via the overflow weir. Electrolyte composition ranged between 61 and 64g/L of Zn and 148 and
30 155 g/L of H_2SO_4 . The neutral feed Mn concentration was 2.0 g/L. Glue concentration was 2.5 mg/L.

 Two central Pg-Ag anodes and four opposing H1S Aluminum cathodes were used. The end cathodes were
35 masked on their back and edges with epoxy resin. The immersed anode dimensions were 6.5 cm x 12 cm. The

- 10 -

immersed cathode dimensions were 9.3 cm x 10.8 cm (central cathodes) and 8.2 cm 11.5 cm (end cathodes). Electrolyte cell volume was 7.3 L. The cathodic current density was set at 440 A/m².

5

Anodic and cathodic overpotentials were measured at preset intervals using a saturated Ag/AgCl reference electrode mounted in a Luggin capillary.

10

Eight continuous tests (Examples 1 to 8 in Table 1) were conducted using "freshly preconditioned anodes" and three cells connected in series. Each of these tests lasted from 43 to 74 hours. Fresh synthetic electrolyte was only used at the beginning of the test (in Example 1). Subsequent tests used the final electrolyte from the previous test.

15

Anodes were preconditioned in a KF-H₂SO₄ electrolyte (34 g/L F, 19 g/L of H₂SO₄) at 40° C at an ACD of 420 A/m² for 24h.

20

The E_h of these cells was controlled as follows:

Cell 1	No E _h control ("Natural E _h conditions")
Cell 2	E _h controlled at 1040 mV
Cell 3	E _h controlled at 1140 mV (occasionally E _h was controlled at lower values)

25

The mud deposited in the bottom and walls of the cell and on the cathode edgesticks was manually removed (with H₂O₂) after the end of Examples 1 (1st Exchange cycle), 3 (3rd Exchange cycle) and 8 (8th Exchange cycle). This was necessary to perform a mass balance on Mn and Pb deportment.

30

Table 1 Summary of Results Obtained in Continuous Experiments 1 to 8											
Examples	EW Cycle hours	Cell No. 1 No Redox Control			Cell No. 2 Eh control at 1040 mV			Cell No. 3 Eh control at 1140 mV			
		CE, %	[Pb] in Zn, ppm	[Mn] drop, g/L	CE, %	[pb] in Zn, ppm	[Mn] drop, g/L	CE, %	[pb] in Zn ppm	[Mn] drop g/L	
1	68.9	87.3	100	0.50	93.4	46	0.60	87.0	39	0.25	
2	42.8	92.0	28	0.40	93.4	41	0.35	92.1	26	0.25	
3	43.3	92.5	17	0.90	93.9	17	0.85	90.5	18	0.60	
4	42.9	77.7	64	0.90	92.2	33	0.70	89.5	30	0.55	
5	45.4	90.3	16	0.85	94.5	22	0.50	89.5	6	0.50	
6	73.5	90.0	13	0.15	94.9	6	0.00	89.1	5	0.00	
7	49.7	91.8	7	0.40	94.9	4	0.30	92.3	6	0.30	
8	47.6	91.2	7	0.40	94.9	4	0.36	92.4	6	0.36	
Average	51.8	89.2	31	0.56	94.1	22	0.46	90.1	17	0.35	

As an indication of the precipitation of insoluble Mn precipitates, the difference in soluble manganese concentration and the average [Mn] in the electrolyte was used:

$$[Mn]_{drop} = [Mn]_{neutral\ feed} - \frac{[Mn]_{initial\ electrolyte} + [Mn]_{final\ electrolyte}}{2}$$

5

The larger the [Mn]_{drop}, the larger the amount of MnO₂ that precipitated in each cell.

Changes in CE, lead deportment to cathode Zn, and [Mn]_{drop} as a function of electrolysis time are shown in Table 1. The continuous run lasted 414 h. E_h control was possible within 50 mV of the set point although excursions as high as 200 mV away from it were often observed. This is attributed to the use of Pt sensing electrodes which are very sensitive to small variations in the concentration of redox species in the electrolyte.

The highest CE values were obtained when the E_h was controlled at about 1040 mV (cell 2). On an average, the CE obtained in cell 2 was 94.1% whereas the CE in cell 1 (a cell without E_h control) averaged only 89.2%. Average CE in cell 3 was 90.1%. E_h values in cell 1 were between 1350 and 1500 mV. In the last four EW cycles (Examples 6 to 8) the CE in cell 2 was very high (94.5% to 94.9%) and reproducible.

While short circuits developed in cell 1 in the first and fourth electrodeposition cycles, no short circuits were detected in cells 2 and 3 in any of the electrodeposition cycles. Deposits obtained with E_h control were polycrystalline and smooth, except in the first cycle in which pitting was observed in all the deposits. In all the experiments, Zn deposits could be

stripped just as easily as those obtained without E_h control.

As shown in Table 1, [Pb] in cathode Zn decreases with electrolysis time. The cells in which the E_h was controlled gave the lowest Pb deportment. On an average, the lowest Pb deportment was obtained in cell 3, followed (in increasing order) by those obtained in cells 2 and 1. It is important to stress that this low Pb deportment was obtained without SrCO_3 additions to any of the cells. Usage of H_2O_2 did not enhance the corrosion rate of the anodes or the Pb content of the cathodic zinc.

From Mn mass balances it was found that the percentage of Mn losses (e.g., "insoluble" manganese leftover in the cell walls and on the anodes) in cells 2 and 3 (25.9% and 20.6%) was smaller than those obtained in cell 1 (28.4%). Furthermore, the total amount of mud formed in the cells with E_h control (6.1 g in cell 2 and 4.1 g in cell 3) was significantly lower than in the cell without E_h control (9.5 g). As shown in Table 1, the [Mn]_{drop} observed in cells 2 and 3 was lower than in cell 1. This provides further evidence that the H_2O_2 treatment is very effective towards MnO_2 solubilization. Although lower [Mn] drops were observed in cells 2 and 3 this did not reflect in increases in Pb deportment, suggesting that H_2O_2 usage could extend the life of the anodes. As the anodes release less Pb into the cathodic Zn, the H_2O_2 consumption decreases, so that at the end of the continuous electrolyte cycle H_2O_2 consumption was as low as 1 Kg H_2O_2 (100%) per ton of Zn. The tests conducted so far, suggests that, on an average basis, 2 Kg of H_2O_2 (100%) per ton of Zn could be required to maximize the CE.

- 15 -

decomposition (H_2O and O_2) are compatible with the Zn EW process. Furthermore, the high selectivity of H_2O_2 to reduce Mn^{3+} and MnO_2 to Mn^{2+} without destroying the PbO_2 layer or the aluminum cathodes (H_2O_2 can be stored in aluminum containers) made the use of H_2O_2 very competitive.

As found in several laboratory experiments, the largest increases in CE with redox control are seen with "new anodes". If MnO_2 formation is reduced, short circuits could be prevented causing an increase in anode life and a decrease in the deportment of lead to the cathodic Zn deposit.

The process above has been described with reference to the electrowinning of a metal from an electrolyte, but it is contemplated that the process can also be applied to electrorefining and electroplating operations.

While only preferred embodiments of the invention have been described herein in detail, the invention is not limited thereby and modifications can be made within the scope of the attached claims.

30

35

WHAT IS CLAIMED IS:

1. A method of counteracting the formation of MnO_2 precipitate in a process for the electrowinning of a metal from an electrolyte, which comprises the steps of:
measuring the redox potential of the electrolyte to obtain a measured value;
comparing the measured value with a predetermined optimum value; and
adding a redox agent to the electrolyte to adjust the redox potential of the electrolyte to the optimum value.
2. The method according to claim 1, wherein the metal is zinc and the redox agent is hydrogen peroxide.
3. The method according to claim 1 or 2, wherein the measuring of the redox potential of the electrolyte comprises measuring the redox potential of a feed stream of electrolyte substantially equivalent to the electrolyte present in an electrolysis cell in which the electrowinning is carried out.
4. The method according to claim 3, wherein the measuring of the redox potential of the feed stream is carried out continuously and the redox agent is added to maintain the measured value substantially equal to the optimum value.
5. The method according to claim 3 or 4, wherein the optimum value falls within a predetermined range and the measured value is maintained at a value within the predetermined range.

- 5 6. The method according to any one of the preceding claims, wherein the redox agent is added by mixing the redox agent with the electrolyte prior to the addition of the electrolyte to the electrolysis cell.
- 10 7. The method according to claim 6, wherein the redox agent is added to cold spent electrolyte which is recycled from the electrolysis cell.
8. The method according to claim 3, wherein the feed stream comprises spent electrolyte from the electrolysis cell.
- 15 9. The method according to claim 3, wherein the feed stream comprises overflow electrolyte from the electrolysis cell.
- 20 10. The method according to claim 3, wherein the measuring of the redox potential of the feed stream is carried out using a pair of electrodes located in the feed stream.
- 25 11. The method according to claim 10, wherein the pair of electrodes comprises a working electrode and a reference electrode.
- 30 12. The method according to claim 11, wherein the working electrode comprises a graphite electrode.
13. The method according to claim 11, wherein the working electrode comprises a platinum electrode.
- 35 14. The method according to claim 1, wherein the redox agent comprises a peroxide.

- 18 -


15. The method according to claim 14, wherein the peroxide is hydrogen peroxide.
- 5 16. The method according to claim 1, wherein the redox agent is added in a continuous fashion.
17. The method according to claim 1, wherein the redox agent is added in a batchwise fashion.
- 10 18. A method of removing MnO_2 precipitate in a process for the electrowinning of a metal from an electrolyte, which comprises the steps of:
measuring the redox potential of the electrolyte to obtain a measured value;
15 comparing said measured value with a predetermined optimum value; and
adding a redox agent to the electrolyte to adjust the redox potential of the electrolyte to said optimum value.
- 20 19. The method according to claim 18, wherein the metal is zinc and the redox agent is hydrogen peroxide.
- 25 20. The method according to claim 18, wherein the redox agent comprises a peroxide.
21. The method according to claim 20, wherein the peroxide is hydrogen peroxide.
- 30 22. The method according to claim 18, wherein the redox agent is added in a continuous fashion.
23. The method according to claim 18, wherein the redox agent is added in a batchwise fashion.
- 35

24. In a zinc electrowinning process, a method of reducing MnO_2 formation in an electrolysis cell, comprising the steps of:
measuring the redox potential of the electrolyte to obtain a measured value;
comparing the measured value with a predetermined optimum value; and
adding a redox agent to the electrolyte to adjust the redox potential of the electrolyte to the optimum value.
25. The method according to claim 24, wherein the redox agent comprises a peroxide.
26. The method according to claim 25, wherein the peroxide is hydrogen peroxide.
27. In a zinc electrowinning process, a method of reducing current efficiency loss in an electrolysis cell, comprising the steps of:
measuring the redox potential of the electrolyte to obtain a measured value;
comparing the measured value with a predetermined optimum value; and
adding a redox agent to the electrolyte to adjust the redox potential of the electrolyte to the optimum value.
28. The method according to claim 27, wherein the redox agent comprises a peroxide.
29. The method according to claim 28, wherein the peroxide is hydrogen peroxide.

30. The method according to claim 24 or claim 27, wherein the cell comprises an anode pickling or aging cell.
- 5 31. In a zinc electrowinning process, a method of continuous on-line cell cleaning of MnO_2 , comprising the steps of:
measuring the redox potential of the electrolyte to
obtain a measured value;
10 comparing the measured value with a predetermined optimum value; and
adding a redox agent to the electrolyte to adjust the redox potential of the electrolyte to the optimum value.
- 15 32. In a zinc electrowinning process, a method of semi-continuous on-line cell cleaning of MnO_2 , comprising the steps of:
measuring the redox potential of the electrolyte to
20 obtain a measured value;
comparing the measured value with a predetermined optimum value; and
adding a redox agent to the electrolyte to adjust the redox potential of the electrolyte to the
25 optimum value.
- 30 33. Apparatus for controlling the redox potential of an electrolyte, comprising:
a redox potential measuring device for measuring the redox potential of an electrolyte to produce an
output measurement value; and
a redox controller responsive to the output
measurement value for controlling the addition of
redox agent to the electrolyte of an electrolysis
35 cell.

- 5 34. The apparatus according to claim 33, wherein the redox potential measuring device comprises a housing for the flow of electrolyte therethrough and a pair of electrodes for measuring the redox potential of an electrolyte flowing through the housing.
- 10 35. The apparatus according to claim 34, wherein the pair of electrolytes comprises a working electrode and a reference electrode.
- 15 36. The apparatus according to claim 35, wherein the working electrode comprises a graphite electrode.
- 20 37. The apparatus according to claim 35, wherein the working electrode comprises a platinum electrode.
- 25 38. The apparatus according to claim 33, wherein the redox potential measuring device comprises a colorimeter for providing an indirect measurement of the redox potential.
- 30
- 35

1/1



SUBSTITUTE SHEET (RULE 26)

INTERNATIONAL SEARCH REPORT

Intern. Application No
PCT/CA 96/00366

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C25C7/06 C25C1/16

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C25C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	FR,A,2 616 159 (OUTOKUMPU OY) 9 December 1988 see page 9; claims 1-8	1
X	US,A,4 211 630 (C.C. BLAKE) 8 July 1980 see column 6 - column 8; claims 1-4	33
A	US,A,4 071 421 (I. M. MASTERS) 31 January 1978 see column 3, line 15 - line 38	1
A	US,A,5 180 563 (WEN-CHAO LAI) 19 January 1993 see column 6, line 15 - line 20	1

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

14 August 1996

Date of mailing of the international search report

02. 09. 96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Groseiller, P

INTERNATIONAL SEARCH REPORT

Information on patent family members

Internat. Application No
PCT/CA 96/00366

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR-A-2616159	09-12-88	AU-B- 1690688 DE-A- 3819020 JP-A- 63312991 NL-A- 8801406	08-12-88 15-12-88 21-12-88 02-01-89
US-A-4211630	08-07-80	GB-A- 1445505 DE-A- 2528140 FR-A,B 2276402 JP-C- 1176934 JP-A- 51018212 JP-B- 58005994 US-A- 4186067	11-08-76 15-01-76 23-01-76 14-11-83 13-02-76 02-02-83 29-01-80
US-A-4071421	31-01-78	CA-A- 1066656 AU-B- 506037 AU-B- 2773477 BE-A- 857654 DE-A- 2736232 FR-A,B 2361482 GB-A- 1525458 JP-A- 53021035 NL-A- 7708712	20-11-79 13-12-79 15-02-79 01-12-77 16-02-78 10-03-78 20-09-78 27-02-78 14-02-78
US-A-5180563	19-01-93	NONE	